
μ SR Study of Magnetism in T'-Structured R_{2-x} Ce_xCuO_{4+ δ}


Crystal structure



Nd₂CuO₄(T')-type structure


apical oxygen can be removed by annealing

Phase diagram



Both Ce-substitution and oxygen reduction degrade magnetic order.

Spin dilution by electron-doping



spin dilution model was proposed for the doping evolution of magnetism. $Pr^{3+} \rightarrow Ce^{4+}$ removal of O^{2-}




Are the effects on magnetism same?

- ☆ evidence of undoped SC
- ☆ evidence of anneal induced change in spin density distribution




precise determination of magnetism in T'-system by µSR measurement

µSR experiment



Clear difference was observed in the time spectrum of AN x=0, and AS x=0.16.

→ Distinct effect of Ce-substitution and oxygen reduction on magnetism.



Non-collinear spin structure with/without Pr moment can well reproduce the internal magnetic field at muon stooping sites.

 $\begin{array}{lll} \text{AS x=0,} & m_{\text{Cu}}{=}0.40\mu_{\text{B,}}\,m_{\text{Pr}}{=}0.07\mu_{\text{B}} \\ \text{AN x=0,} & m_{\text{Cu}}{\sim}0.3\mu_{\text{B,}}\,m_{\text{Pr}}{=}0.05\mu_{\text{B}} \\ \text{AS x=0.16,} & m_{\text{Cu}}{\sim}0.15\mu_{\text{B,}}\,m_{\text{Pr}}{\sim}0\mu_{\text{B}} \end{array}$

Pr-Cu interaction is suppressed by Cesubstitution, suggesting the enhancement of two dimensionality by electron-doping.